



Storage Recommendations for **Avian-D and Avian-Black-S Coating**

- Storage recommendations are the same for the Avian Black S and Avian D coating. Both are water-based urethanes with (obviously) different pigments.
- Both coatings (unopened) have a recommended shelf life of one year.
- Part B for both should be refrigerated after opening and should be used as soon as possible after opening.
- Part A can be stored at room temperatures but the temperature should not fluctuate. Hot or cold temperatures do affect the coating. Recommended storage is in indoor laboratory situation in a cabinet.
- The pigment can settle with storage and the coating should be thoroughly mixed prior to use (either a mechanical paddle stirrer or a paint can shaker). Black coating that is not mixed thoroughly will appear to have a glossy sheen. If the coating is not matte, remix to get particles into suspension.
- Lids should be cleaned off prior to replacing on the cans for storage.